

PRODUCT DATA SHEET

Rev.03/Effective Date: Jul 11, 2022



DUCKHAMS ZIRCON Z68 ANTI-WEAR

DUCKHAMS ZIRCON Z68 ANTI-WEAR is a premium quality, anti-wear hydraulic fluid designed to meet the requirements of fluid power system. Hydraulic Oil # 68 is formulated with high quality base oil and selected additives to provide superior performances in filterability, pump wear protection in dry and wet conditions and oxidation stability

Meet Performance:

- Denison HF-0, HF-1, HF-2
- Eaton Brochure 694 for 35VQ25A (Vickers product) Vickers 104C
- DIN 51524 part II (HLP)
- AFNOR NF E 48-603 (HM)
- FZG A/8.3/90 (FLS 10)
- Cincinnati Machine P-68, P-70, P-69
- GM L52
- ISO 11158 Categories HM
- ASTM D6158 Type HM
- Other industry specification add on US Steel (AIST) 127,136

Applications:

- All hydraulics systems with vane, gear or piston pumps
- Hydraulics of mobile and construction equipment
- Plastic injection molding machines
- Industrial circulating systems

Features and Benefits:

- Excellent anti-wear properties and minimize metal-to-metal contact.
- Excellent protection on corrosion from both copper and steel.
- Minimize rust problems by very fast release of water.
- Good oxidation stability, provide good service life in high pressure service.
- Good foam inhibitor, minimize foaming and aeration problems.
- This product designed for major pump manufacturers of both vane and piston pumps.

Typical Properties:

| Properties | TestMethod | Typical value |
|---|----------------------|----------------|
| Appearance | Visual | Bright & Clear |
| ASTM Color | ASTM D1500/D6045 | L1.0 |
| Density @15°C, g/cm³ | ASTM D4052 | 0.8850 |
| Kinematic Viscosity @40°C | ASTM D445 | 67.17 |
| Kinematic Viscosity @100°C | ASTM D445 | 8.654 |
| Viscosity Index | ASTM D2270 | 100 |
| Flash Point by COC, °C | ASTM D92 | 232 |
| Pour Point, °C | ASTM D5950/6892/6749 | -6 |
| Demulsibility @54°C ml/ml/ml (min) | ASTM D1401 | 40-40-0 (15) |
| Zn Content | ASTM D6481/D4951 | 0.019 |
| Foaming: Seq.I @24°C, Tendency/Stability | ASTM D892 | 0/0 |
| Foaming: Seq.II @93.5°C, Tendency/Stability | ASTM D892 | 0/0 |
| Foaming: Seq.III @24°C after 93.5°C, Tendency/Stability | ASTM D892 | 0/0 |

These descriptions are typical of current production. Whilst future production will conform to Duckhams' specification, variations in there description may occurs.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use.

Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material. Freedom to use any patent owned by Duckhams or others is not to be inferred from any statement contained herein.

